

Primary Name GLACIER BUFF MINNESOTA STONE, FLEURI CUT

Type of Stone Limestone (Dolomite\*)  
\* (As defined by ASTM C-119)

Country of Origin United States of America

Quarry Location Kasota Township, Le Sueur County, Minnesota

Quarry Number \_\_\_\_\_

Geological Formation Ordovician

Color Range ( Y/G ) Yellow or Gold

Description \_\_\_\_\_

\_\_\_\_\_

\_\_\_\_\_

Recommended Usage: Exterior X Interior X

**TECHNICAL INFORMATION**

	VALUE		ASTM** Test Method
	English	Metric	
Absorption by weight, %	4.1	4.1	C97
Density, lbs/ft <sup>3</sup> , (kg/m <sup>3</sup> )	153.6	2,460.44	C97
Compressive strength, psi, (MPa)	10,590.	73.03	C170
Abrasion resistance, hardness	15.8	No Value Established	C241
Flexural strength, psi, (MPa)	1,030.	7.1	C880

MIA Classification for Soundness \_\_\_\_\_ (Marble Only)

Other Trade Names \_\_\_\_\_

Color plate and information supplied by: **Vetter Stone Company**  
**Kasota, Minnesota**

NOTE: Although every effort has been made to depict an accurate representation of the sample, some variations may be present due to the nature of the printing process.

Technical details provide a frame of reference only. Because stone is a product of nature, testing to determine specific physical qualities should be repeated for each major project.

Control Number 257

\*\*American Society for Testing and Materials; standards developed by Committee C18