

Primary Name NORTHERN BUFF MINNESOTA STONE, VEINE CUT

Type of Stone Limestone (Dolomite*)
* (As defined by ASTM C-119)

Country of Origin United States of America

Quarry Location Kasota Township, Le Sueur County, Minnesota

Quarry Number _____

Geological Formation Ordovician

Color Range (Y/G) Yellow or Gold

Description _____

Recommended Usage: Exterior X Interior X

TECHNICAL INFORMATION	VALUE		ASTM** Test Method
	English	Metric	
Absorption by weight, %	3.87	3.87	C97
Density, lbs/ft ³ , (kg/m ³)	150.44	2,409.82	C97
Compressive strength, psi, (MPa)	8,230.	56.76	C170
Abrasion resistance, hardness	11.8	No Value Established	C241
Flexural strength, psi, (MPa)	1,350.	9.31	C880

MIA Classification for Soundness _____ (Marble Only)

Other Trade Names Kasota Buff

Color plate and information supplied by: **Vetter Stone Company**
Kasota, Minnesota

NOTE: Although every effort has been made to depict an accurate representation of the sample, some variations may be present due to the nature of the printing process.

Technical details provide a frame of reference only. Because stone is a product of nature, testing to determine specific physical qualities should be repeated for each major project.

Control Number 262

**American Society for Testing and Materials; standards developed by Committee C18