

Primary Name MINNESOTA TRAVERNELLE, VEINE CUT
 Type of Stone Limestone (Dolomite*)
* (As defined by ASTM C-119)
 Country of Origin United States of America
 Quarry Location Lime Township, Blue Earth County, Minnesota
 Quarry Number _____
 Geological Formation Ordovician
 Color Range (Brw) Brown
 Description A veined stone with random-sized travertine-like voids
Brown to pink tones
 Recommended Usage: Exterior Interior

TECHNICAL INFORMATION

	VALUE		ASTM** Test Method
	English	Metric	
Absorption by weight, %	3.2	3.2	C97
Density, lbs/ft ³ , (kg/m ³)	152.88	2,448.9	C97
Compressive strength, psi, (MPa)	13,000.	89.66	C170
Abrasion resistance, hardness	16.4	No Value Established	C241
Flexural strength, psi, (MPa)	1,420.	9.79	C880

MIA Classification for Soundness _____ (Marble Only)

Other Trade Names _____

Color plate and information supplied by: **Vetter Stone Company**
Kasota, Minnesota

NOTE: Although every effort has been made to depict an accurate representation of the sample, some variations may be present due to the nature of the printing process.
 Technical details provide a frame of reference only. Because stone is a product of nature, testing to determine specific physical qualities should be repeated for each major project.

Control Number 261

**American Society for Testing and Materials; standards developed by Committee C18