

Primary Name NORTHERN CREAM, MINNESOTA STONE, FLEURI CUT

Type of Stone Limestone (Dolomite*)
* (As defined by ASTM C-119)

Country of Origin United States of America

Quarry Location Kasota Township, Le Sueur County, Minnesota

Quarry Number 2100772

Geological Formation Ordovician

Color Range (Bf-C/L) Buff-Cream or Light

Description Characterized by random sized and dispersed geodes

Recommended Usage: Exterior Interior

TECHNICAL INFORMATION	VALUE		ASTM** Test Method
	English	Metric	
Absorption by weight, %	5.2	5.2	C97
Density, lbs/ft ³ , (kg/m ³)	148.51	2,378.9	C97
Compressive strength, psi, (MPa)	7,900.	54.48	C170
Abrasion resistance, hardness	14.1	No Value Established	C241
Flexural strength, psi, (MPa)	1,210.	8.34	C880

MIA Classification for Soundness _____ (Marble Only)

Other Trade Names _____

Color plate and information supplied by: **Vetter Stone Company**
Kasota, Minnesota

NOTE: Although every effort has been made to depict an accurate representation of the sample, some variations may be present due to the nature of the printing process.

Technical details provide a frame of reference only. Because stone is a product of nature, testing to determine specific physical qualities should be repeated for each major project.

Control Number 263

**American Society for Testing and Materials; standards developed by Committee C18