

Primary Name NORTHERN PINK BUFF MINNESOTA STONE,  
FLEURI CUT, PINK RANGE

Type of Stone Limestone (Dolomite\*)  
\* (As defined by ASTM C-119)

Country of Origin United States of America

Quarry Location Kasota Township, Le Sueur County, Minnesota  
Lime Township, Blue Earth County, Minnesota

Quarry Number 2100772  
2100086

Geological Formation Ordovician

Color Range ( Bf-C/L ) Buff-Cream or Light

Description Beige with creamy variations

Recommended Usage: Exterior X Interior X

**TECHNICAL INFORMATION**

	VALUE		ASTM** Test Method
	English	Metric	
Absorption by weight, %	4.38	4.38	C97
Density, lbs/ft <sup>3</sup> , (kg/m <sup>3</sup> )	153.38	2,456.91	C97
Compressive strength, psi, (MPa)	8,850.	61.03	C170
Abrasion resistance, hardness	13.6	No Value Established	C241
Flexural strength, psi, (MPa)	1,290.	8.9	C880

MIA Classification for Soundness \_\_\_\_\_ (Marble Only)

Other Trade Names \_\_\_\_\_

Color plate and information supplied by: **Vetter Stone Company**  
**Kasota, Minnesota**

NOTE: Although every effort has been made to depict an accurate representation of the sample, some variations may be present due to the nature of the printing process.

Technical details provide a frame of reference only. Because stone is a product of nature, testing to determine specific physical qualities should be repeated for each major project.

Control Number 267

\*\*American Society for Testing and Materials; standards developed by Committee C18