

Primary Name ALABAMA VEINED LIMESTONE

Type of Stone Limestone
*(As defined by ASTM C-119)

Country of Origin United States of America

Quarry Location Franklin County, Alabama

Quarry Number _____

Geological Formation Mississippian

Color Range (Bf-C/L) Buff - Cream or Light

Description Warm color with uniform texture and unique delicate shadow veins.

Producer's Recommended Usage: Exterior Interior

Average Block size: 12'-0" Length X 5'-0" Width X 5'-6" Height

Average Fabricated Slab size: 10'-0" Length X 5'-6" Width

Available in Thin Tile: _____ Yes No

Maximum Thin Tile size: N/A Length X _____ Width X _____ Thickness

TECHNICAL INFORMATION

	VALUE		ASTM** Test Method
	English	Metric	
Absorption by weight, %	5.23	5.23	C97
Density, lbs/ft ³ , (kg/m ³)	141.52	2,268.	C97
Compressive strength, psi, (MPa)	4,272.	29.45	C170
Abrasion resistance, hardness	6.75	No Value Established	C241
Flexural strength, psi, (MPa)	845.	5.82	C880

MIA Classification for Soundness _____ (Marble Only)

Other Trade Names _____

NOTE: Although every effort has been made to depict an accurate representation of the sample, some variations may be present due to the nature of the printing process.

Technical details provide a frame of reference only. Because stone is a product of nature, testing to determine specific physical qualities should be repeated for each major project.

Control Number II-112

**American Society for Testing and Materials; standards developed by Committee C18

© Copyright 1993; DIMENSION STONES OF THE WORLD© - Volume II; Marble Institute of America printed in U.S.A.